

X

इंटरनेट

# Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

"जानने का अधिकार, जीने का अधिकार" Mazdoor Kisan Shakti Sangathan "The Right to Information, The Right to Live"

"पुराने को छोड नये के तरफ" Jawaharlal Nehru "Step Out From the Old to the New"

मानक

IS 3822 (2002): Eye Hooks for Use with Chains [MED 14:

Made Available By Public.Resource.Org

"ज्ञान से एक नये भारत का निर्माण″ Satyanarayan Gangaram Pitroda "Invent a New India Using Knowledge"

Cranes, Lifting Chains and Related Equipment]

RIGHT TO INFORMATION "ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता Bhartrhari-Nītiśatakam "Knowledge is such a treasure which cannot be stolen"





# BLANK PAGE



PROTECTED BY COPYRIGHT

भारतीय मानक जंजीर के साथ प्रयुक्त आई हुक – विशिष्टि ( दूसरा पुनरीक्षण )

# Indian Standard EYE HOOKS FOR USE WITH CHAINS — SPECIFICATION (Second Revision)

ICS 53.020.30

© BIS 2002

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

**Price Group 3** 

#### FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Cranes and Lifting Chains Sectional Committee had been approved by the Mechanical Engineering Division Council.

This standard was first published in 1966 and revised in 1982. The second revision of this standard was taken up, since a need was felt by the industry to revise the standard to incorporate the increased safe working load limits and to reduce the sulphur and phosphorus limits for Grade L and Grade M hooks.

During manufacturing of the hook, a single piece forging has been introduced to increase the longevity. The construction details and the complicated dimensional details of the hook are left to the choice of the manufacturers and dimensional tolerances eliminated completely. The radiographic/ultrasonic tests on the hook have been deleted.

The composition of the Committee responsible for formulation of this standard is given in Annex A.

For the purpose of deciding whether a particular requirements of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2: 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

# Indian Standard

# EYE HOOKS FOR USE WITH CHAINS — SPECIFICATION

# (Second Revision)

#### **1 SCOPE**

1.1 This standard covers basic requirements, materials and dimensions of mild steel, high tensile steel and alloy steel eye hooks for use, with Grade L(3), Grade M(4), and Grade S(6) and Grade T(8) chains respectively.

1.1.1 This standard applies to the drop-forged and open-die forged eye hooks up to a safe working load of 63 000 kg.

#### **2 REFERENCES**

The following Indian Standards contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below:

IS No.	Title				
1500 : 1983	Method for Brinell hardness test for metallic materials (second revision)				
1875 : 1992	Carbon steel billets, blooms, slabs and bars for forging ( <i>fifth</i> revision)				
4367 : 1991	Alloy steel forgings for general industrial use ( <i>first revision</i> )				
4748 : 1988	Method for estimating average grain size of metal (first revision)				
7847 : 1975	General characteristics of lifting hooks				

#### **3 TERMINOLOGY**

For the purpose of this standard, the definitions given in IS 7847 shall apply.

#### **4 RATING**

The hooks shall be rated according to the safe working load for a particular grade given in Table 1.

#### **5 MATERIALS**

5.1 The steel shall be produced by the open hearth or electric process or by any oxygen top blown process.

5.2 In its finished state, as supplied to the hook manufacturer, the steel shall be fully killed and shall meet the maximum sulphur and phosphorus content limits as under:

		Cast Analysis (Percent), Max	Check Analysis (Percent), Max
a)	For Grade L and M he	ooks	
	Sulphur	0.045	0.050
	Phosphorus	0.040	0.045
b)	For Grade S and T ho	oks	
	Sulphur	0.035	0.040
	Phosphorus	0.035	0.040

**5.3** The steel shall be made in conformity with a suitable de-oxidation practice to obtain an austenitic grain size of 5 or finer when tested in accordance with IS 4748.

5.3.1 This could be accomplished, for example, by ensuring that it contains sufficient aluminium, or an equivalent element to enable the manufacture of hooks stabilized against strain and age-embrittlement during service, a minimum of 0.02 percent of metallic aluminium is quoted for guidance.

5.4 Within the above limitations it is the responsibility of the hook manufacturers to select steel, so that the finished hook, suitably heat-treated, meets the mechanical properties required by this specification. Class 1A and Class 3 steels of IS 1875 may be used for Grade L and Grade M hooks respectively. Alloy steel conforming to IS 4367 may be used for Grade Sand Grade T hooks. Any other material having equivalent mechanical properties may also be used.

## **6 SHAPE AND DIMENSIONS**

The shape and dimensions of hook shall be within the maximum and minimum limits specified in Table 1 and generally according to Fig. 1.

In addition, the following requirements shall be met:

a) The point height  $B_s$  shall be greater than the actual throat opening, G of the same hook (see Fig. 1).

# Table 1 Mechanical and Dimensional Characteristics of Eye Hooks

(Clauses 4, 6, 9 and 10.1; and Fig. 1)

A 11	11	•	•	****
AII	dimer	isions	1n	millimetres.
	_			

	Nominal Dia Chain		Lifting Ca Tonnes fo	apacity in or Grades		Proof Load ' <i>Fe</i> ' in kN for Grades			Throat2.7 d_nSeat IOpeningMin3.8 a2.9 d_nMir			Section Depth 4.3 d <sub>n</sub>	Section Width 2.9 d <sub>n</sub>	1.75 d <sub>n</sub> Min	1.8 d <sub>n</sub> Max	15.5 d <sub>n</sub> Max	
	d_	L	М	S	Т	Ĺ	м	S	T	Min G	G.	D	Max H	Max L	E	F	L
	(1)	(2)	(3)	(4)	(5)	(6)	(7)	 (8)	(9)	(10)	(11)	(12)	(13)	 (14)	(15)	(16)	(17)
	6.0	0.50	0.63	1.00	1.25	10.00	12.50	20.00	25.00	17.40	16.20	22.80	25.80	17.40	10.50	10.80	93.00
	7.1	0.63	0.80	1.25	1.60	12.50	16.00	25.00	31.50	20.60	19.20	27.00	30.50	20.60	12.40	12.80	110.00
	8.0	0.80	1.00	1.60	2.00	16.00	20.00	31.50	40.00	23.20	21.60	30.40	34.40	23.20	14.00	14.40	124.00
	9.0	1.00	1.25	2.00	2.50	20.00	25.00	40.00	50.00	26.10	24.30	34.20	38.70	26.10	15.80	16.20	139.50
	10.0	1.25	1.60	2.50	3.20	25.00	31.50	50.00	63.00	29.00	27.00	38.00	43.00	29.00	17.50	18.00	155.00
2	11.0	1.60	2.00	3.20	4.00	31.50	40.00	63.00	80.00	31.90	29.70	41.80	43.70	31.90	19.30	19.80	170.50
	12.0	2.00	2.50	4.00	5.00	40.00	50.00	80.00	100.00	34.80	32.40	45.60	51.60	34.80	21.00	21.60	186.00
	14.0	2.50	3.20	5.00	6.30	50.00	63.00	100.00	125.00	40.60	37.80	53.20	60.20	40.60	24.50	25.20	279.00
	16.0	3.20	4.00	6.30	8.00	63.00	80.00	125.00	160.00	46.40	43.20	60.80	68.80	46.40	28.00	28.80	248.00
	18.0	4.00	5.00	8.00	10.00	80.00	100.00	160.00	200.00	52.20	48.60	68.40	77.40	52.20	31.50	32.40	279.00
	20.0	5.00	6.30	10.00	12.50	100.00	125.00	200.00	250.00	58.00	54.00	76.00	86.00	58.00	35.00	36.00	310.00
	22.0	6.30	8.00	12.50	16.00	125.00	160.00	250.00	315.00	65.00	59.40	83.60	94.60	63.80	38.50	39.60	341.00
	25.0	8.00	10.00	16.00	20.00	160.00	200.00	315.00	400.00	72.20	67.50	95.00	107.50	72.50	43.80	45.00	387.50
	28.0	10.00	12.50	20.00	25.00	200.00	250.00	400.00	500.00	81.20	75.60	106.40	120.40	81.20	49.00	50.40	434.00
	32.0	12.50	16.00	25.00	32.00	250.00	315.00	500.00	630.00	92.80	86.40	121.60	137.60	92.80	56.00	57.60	496.00
	36.0	16.00	20.00	32.00	40.00	315.00	400.00	630.00	800.00	104.40	97.20	136.80	154.80	104.40	63.00	64.80	558.00
	40.0	20.00	25.00	40.00	50.00	400.00	500.00	800.00	1000.00	116.00	108.00	152.00	172.00	116.00	70.00	72.00	620.00
	45.0	25.00	32.00	50.00	63.00	500.00	630.00	1000.00	1260.00	130.50	121.50	171.00	193.00	130.50	78.80	81.00	697.50

ī.

- b) The actual throat opening G shall not exceed 95 percent of the actual seat diameter D of the same hook.
- c) The minimum value for E specified in table (that is  $1.75 d_n$ ) applies to hooks used in all welded slings. For hooks used in slings assembled by methods other than welding, the minimum value shall be  $1.9 d_n$ .
- d) If any safety latch is fitted, it shall be capable of closing over the maximum diameter of the

bar which can be admitted through the actual opening  $G_1$  as indicated by the dotted lines in Fig. 1.

## 7 WORKMANSHIP AND FINISH

The hooks shall be free from defects and shall be cleanly forged in one piece in such a manner that the macro etched flaw lines follow the body of the hook except at the eye. The finished hook shall be clean and free from coating of any description, unless otherwise specified by the purchaser.



FIG. 1 DIMENSIONS OF HOOK

#### IS 3822 : 2002

# **8 HEAT TREATMENT**

8.1 All hooks shall, before proof testing, be subjected to one of the following heat treatments:

- a) Normalizing by heating to a temperature within 50°C above the upper critical point of the steel used, followed by cooling in still air; or
- b) Hardening by heating to a temperature within 50°C above the upper critical point of the steel used, followed by quenching in oil or water and tempering.

**8.1.1** Normalizing treatment shall be permitted for Grade L hooks and Grade M hooks only. Grade S hooks and Grade T hooks shall be hardened and tempered necessarily.

**8.1.2** The minimum hardness of hooks after heat treatment, when tested according to the method given in IS 1500, shall be 250 HB and 350 HB for Grade S and Grade T respectively. This test shall be carried out on the hooks selected for destructive testing.

**8.2** Details of heat treatment given to the hooks during manufacture shall be endorsed on the manufacturer's test certificate.

#### **9 PROOF TESTING**

After heat treatment and other processing, the finished hooks shall be subjected to proof load of twice the safe working load as given in Table 1. Prior to the application of the proof load, each hook shall bear two centre punch marks at positions 'a' and 'b' as shown in Fig. 1. The change in distance between 'a' and 'b' before applying proof load and after removal of the proof load will be the amount of permanent deformation up to 0.5 percent of the actual throat or the dimension between 'a' and 'b' or 0.2 mm whichever is higher. After removal of the proof load and determination of the permanent set, each hook shall be thoroughly examined by a competent person and shall be accepted as complying with the standard if no permanent deformation or visible defects are observed on the hook.

#### **10 DESTRUCTION TEST**

10.1 A sample hook shall be selected out of a lot of every 50 hooks or less and tested to four times the safe working load specified for the appropriate grade hook in Table 1. The load shall be applied as specified in 7.3 of IS 7847. The hook shall withstand any load less than four times the safe working load, neither fracture nor so distort as to be incapable of retaining the load. NOTE — It is not necessary to test the hook up to its actual ultimate strength for mechanical properties to be demonstrated. It is sufficient that the minimum ultimate strength specified is exceeded and the hook deforms significantly at the maximum force of the test.

#### 10.2 Micro-Structure Test

After destruction test, a portion of the hook, which has not undergone deformation, shall be taken and micro-structure test shall be carried out to ensure that hooks have been given proper heat treatment.

## **10.3 Hardness Testing**

Hook of Grade S and Grade T selected for destructive testing shall be tested for hardness value as given in 8.1.2. The hardness shall be checked at least 10 mm away from the edge and 1 mm below the surface.

# 11 INSPECTION, CERTIFICATE OF TEST AND EXAMINATION

11.1 The representative of the purchaser shall have access to the works of the manufacturer at all reasonable times for the purpose of witnessing the specified tests and inspecting the machine and method of examination. The manufacturer shall give the inspector copies of the reports of the tests made in his presence.

**11.2** The manufacturer shall supply a certificate of test and examination in accordance with **8.2** and **8.3** of IS 7847.

#### **12 MARKING**

12.1 Provided that the hook passes the proof test, each hook shall be legibly and indelibly marked on parts not highly stressed. This marking shall include at least the following information:

- a) Chain size,
- b) Grade letter,
- c) Safe working load, and
- d) Manufacturer's identification mark.

#### 12.2 BIS Certification Marking

The hook may also be marked with the Standard Mark.

**12.2.1** The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act*, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the license for the use of the Standard Mark may be granted to the manufacturers or producers may be obtained from the Bureau of Indian Standards.

2.1

# ANNEX A

#### (Foreword)

#### **COMMITTEE COMPOSITION**

#### Cranes and Lifting Chains Sectional Committee, MED 14

#### Organization

Bharat Heavy Electricals Ltd, Tiruchirappalli Armsel Metal Pvt Ltd, Bangalore

Auri Industries India (P) Ltd, Pune

Bharat Heavy Electricals Ltd, Hyderabad

Bhartiya Cutler-Hammer, Faridabad

Braithwaite and Co Ltd, Kolkata

Central Building Research Institute, Roorkee

Coal India Ltd, Kolkata

- Directorate General, Factory Advice Service and Labour Institute, Mumbai
- Directorate General of Supplies and Disposals, New Delhi

Escorts Construction Equipment Ltd, Faridabad

Furnance and Foundry Equipment Co, Mumbai Hercules Hoists Ltd, Mumbai

Hindustan Shipyard Ltd, Visakhapatnam

Indian Chain Pvt Ltd, Kolkata

Indian Link Chain Manufacturers Ltd, Mumbai Jessop and Co Ltd, Kolkata

Larsen and Toubro Limited, Kolkata

Lifting Equipment and Accessories Ltd, Delhi Mega Drives Pvt Ltd, Thane

Metallurgical and Engineering Consultants (I) Ltd, Ranchi

M. N. Dastur and Co Ltd, Kolkata

#### Representative(s)

SHRI K. MANICKAM ( Chairman )

SHRI A. C. HERI SHRI N. VASUDEVA (Alternate)

SHRI M. N. DANTWALA

- SHRI GIRISH SHRIVASTAVA SHRI M. SUBBA RAO ( *Alternate* )
- SHRI V. RAMACHANDRAN SHRI VIRENDER SINGH (Alternate)
- Shri S. K. Gangopadhyay Shri A. P. Saha (*Alternate*)
- SHRI R. L. GUPTA SHRI D. K. GAUTAM (Alternate)

SHRI R. DASGUPTA

- SHRI M. A. BALAKRISHNAN SHRI G. M. K. RAJ ( Alternate )
- SHRI R. C. GUPTA SHRI J. K. KHANNA (Alternate)
- SHRI PRADEEP K. TYAGI SHRI RAVINDRA LUTHRA ( Alternate )

SHRI SHYAM M. GURNANI

- SHRI P. B. KUCHERIA SHRI H. A. NEVATIA (Alternate)
- SHRI D. V. S. N. RAJU SHRI B. KRISHNAPPA (Alternate)
- Shri P. Chitlangia Shri Lalitmohan ( *Alternate* )

SHRI P. K. NEVATIA

- SHRI BIMAL CHANDRAPAL SHRI TAPAN DATTA ( Alternate )
- SHRI M. S. CHAKRABORTHY SHRI L. N. MISHRA (Alternate)

SHRI RAJIV KHETAN

- SHRI MAJUMDAR SHRI N. B. BHUJLE (Alternate)
- SHRI T. K. ROY SHRI H. S. SINGH (Alternate)
- SHRI D. GHOSH SHRI G. C. BANERJEE (Alternate)

5

#### IS 3822 : 2002

(Continued from page 5)

Organization Ministry of Defence ( DGI ), New Delhi

Ministry of Surface Transport, New Delhi Mukand Ltd, Thane

National Thermal Power Corporation Ltd, New Delhi

Project and Development India Ltd, Dhanbad

Research Designs and Standards Organization, Lucknow Reva Engineering Industrial (P) Ltd, New Delhi

Southern Structural Ltd, Chennai

Steel Authority of India Ltd, Bhilai

Tata Engineering and Locomotive Co Ltd, Pune

Tata Iron and Steel Company Limited, Jamshedpur

Tractor India Ltd, Kolkata

Tractel Tirfor (India) Ltd, New Delhi

Unicon Technology International Pvt Ltd, New Delhi

WMI Cranes Ltd, Mumbai BIS Directorate General Representative(s)

SHRI K. PARTHIBAN SHRI RAJINDER SINGH ( Alternate )

SHRI T. K. DATTA

SHRI D. CHAKRABORTHY SHRI D. S. SENTHILVEL (Alternate)

SHRI B. K. BHATTACHARYA SHRI R. S. YADAV (Alternate)

SHRI L. C. DADLANI SHRI R. N. PRASAD (Alternate)

SHRI R. N. HALDAR

SHRI BALRAJ GOBE

SHRI J. KUMARAN SHRI C. SELVAKUMAR (Alternate)

SHRI K. DHARMARAJAN SHRI M. K. MUKHERJEE ( Alternate )

SHRI R. K. JOSHI SHRI S. MISHRA (Alternate)

SHRI D. P. RATHORE SHRI J. P. SINGH (Alternate)

SHRI SRIMANTA DATTA SHRI A. K. HALDER ( *Alternate* )

Dr P. K. CHAKRAVARTY SHRI SAURABH RAJOURIA (Alternate)

SHRI R. S. NALWA SHRI MANISH NALWA (Alternate)

SHRI S. M. MALANI

SHRI M. L. CHOPRA, Director and Head (MED) [Representing Director General (*Ex-Officio*)]

Member-Secretary SHRI S. B. ROY Director (MED), BIS

#### **Bureau of Indian Standards**

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

## Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

## **Review of Indian Standards**

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards : Monthly Additions'

This Indian Standard has been developed from Doc : No. ME 14 (0333).

## Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected
4. T		
·····		
	·	·
· 1	BUREAU OF INDIAN STANDAR	RDS
Headquarters:		
Manak Bhavan, 9 Bahadur Shah Telephones : 323 01 31, 323 33 7	Zafar Marg, New Delhi 110 002 5, 323 94 02	Telegrams: Manaksanstha (Common to all offices)
Regional Offices :		Telephone
Central: Manak Bhavan, 9 Baha NEW DELHI 110002	dur Shah Zafar Marg	323 76 17     323 38 41
Eastern: 1/14 C. I. T. Scheme V KOLKATA 700 054	II M, V. I. P. Road, Kankurgachi	<b>{</b> 337 84 99, 337 85 61 337 86 26, 337 91 20
Northern: SCO 335-336, Sector 3	4-A, CHANDIGARH 160 022	{     60 38 43     60 20 25
Southern : C. I. T. Campus, IV C	oss Road, CHENNAI 600 113	Example 254 12 16, 254 14 42     254 25 19, 254 13 15     Example 254 25 19, 254 13 15
Western : Manakaiaya, E9 MID MUMBAI 400 093	C, Marol, Andheri (East)	832 92 95, 832 78 58     832 78 91, 832 78 92
Branches : AHMADABAD. I	ANGALORE. BHOPAL. BHUBAN	NESHWAR, COIMBATORE

Fancnes : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. NALAGARH. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM.